

FLAME-RETARDANT STYRENIC RESIN COMPOSITION

Patent Number: JP8092445
Publication date: 1996-04-09
Inventor(s): IWATA KEIKO; FUJITA TOMOYUKI
Applicant(s): ASAHI CHEM IND CO LTD
Requested Patent: ☐ JP8092445

Application Number: JP19940226565 19940921

Priority Number(s):

IPC Classification: C08L25/04 ; C08K3/22 ; C08K5/03 ; C08K5/06

EC Classification:

Equivalents:

Abstract

PURPOSE: To obtain a flame-retardant styrenic resin compsn. excellent in flame retardance and the balance among heat resistance, impact resistance, and flowability by compounding a styrenic resin with two specific halogenous flame retardants, an auxiliary flame retardant, and a small amt. of polytetrafluoroethylene.

CONSTITUTION: This resin compsn. comprises 100 pts.wt. styrenic resin (A), 2-18 pts.wt. halogenated arom. -diol-based ether deriv. (B) having a wt.-average mol.wt. of 500-10,000 [a compd. of formula I (wherein R is H, a group of formula II, etc.; X is Br or Cl; (l), (j), (k), and (m) are each 1-4; and (n) is 0-30)], 2-16 pts.wt. polyhalogenated diphenylalkane (C) of formula III [wherein X is Br or Cl; (l) and (m) are each 0-6 excluding the case where they are both 0; and R is C_nH_{2n} (wherein (n) is 1-10)], 1-10 pts.wt. Sb₂O₃ (D), and 0.01-0.5 pt.wt. polytetrafluoroethylene (E), the sum of components B and C being 12-21 pts.wt. Thus, a compsn. excellent in flame retardance and the balance among heat resistance, impact resistance, and flowability is obtd. with a reduced amt. of halogenous flame retardants.

Data supplied from the esp@cenet database - 12